

### PRODUCT SPECIFICATION SHEET CLOSED CELL POLYETHYLENE FOAM, CFC AND HCFC FREE

Physical Properties	Test Method	Unit	Value
Nominal Density	ASTM D3575-08 Suffix W ISO 845:2006	Kg/m <sup>3</sup>	30
Compressive Strength Vertical @ 25% Vertical @ 50%	ASTM D3575-08 Suffix D ISO 7214:2007	KPa	10 24
Compressive Strength 25% (4th compression) 50% (4th compression) 70% (4th compression) (100mm/min compression speed)	ISO 3386 1986 part 1 DIN 53577	KPa	3 13 50
Compression Set	ASTM D3575-08 Suffix B (50% Compression) ISO 1856:2000 (25% compression)	%	< 30 < 20
Cell Size	BS 4443/1 Met.4	Cells/25mm	< 10
Fire test-response Characteristics (1)			
Building & Construction	DIN 4102	Class	B2
Traffic Noise barriers	EN 1794-2	Class	1
Thermal Conductivity @ 23°C (73°F) @ -5°C (23 °F)	ASTM D3575-08 Suffix V ISO 8301	W/mK W/mK	0.104 0.082
Thermal stability (24hrs at 70°C)	ASTM D3575-08 Suffix S ISO 2796	%	< 3
Water Pick Up by Diffusion (RH > 95% - after 28 days)	UNI EN 12088	Kg/m <sup>2</sup>	< 3
Water Pick Up by Diffusion (RH > 95% - after 28 days)	UNI EN 12088	Volume %	< 5
Tensile Strength @ Peak	ASTM D3575 Suffix T ISO1798	KPa	130
Tensile Elongation	ASTM D3575 Suffix T ISO1798	%	70
VOC Emissions	AFNOR NF EN ISO 16000-9	Class	A+
Working temperature	-	°C	-60 +80
Airflow Resistance	UNI EN 29053:1994	Pa.S/m <sup>3</sup> = Rayls/m <sup>2</sup>	510,000 (25mm) 2,785,000 (50mm)

(1) These numerical laboratory fire-test-response characteristics are not intended to reflect hazards presented by this material under actual fire conditions

**ACCELERATED AGEING TEST REPORTS IN QUV-CHAMBER AVAILABLE UPON REQUEST.**

NOTICE: While values shown are typical of this product, they should not be construed as specification limits. Sealed Air makes no warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, with respect to any product, information or recommendations referred to herein, and shall not be liable for any loss or damage, directly or indirectly, related to such product, information or recommendations or for consequential or incidental damages. User should test each application to determine suitability of the product for the intended use.